

**PATENT ABSTRACTS OF JAPAN**(11)Publication number : **09-157771**(43)Date of publication of application : **17.06.1997**

(51)Int.Cl.

**C22C 1/05  
C04B 35/645**(21)Application number : **07-345612**(71)Applicant : **CHICHIBU ONODA CEMENT  
CORP**(22)Date of filing : **08.12.1995**(72)Inventor : **UZAWA MASAMI  
KYODA MAKOTO****(54) PRODUCTION OF HARD COMPOSITE MATERIAL CONTAINING CUBIC BORON NITRIDE**

(57)Abstract:

**PROBLEM TO BE SOLVED:** To provide a high-density composite material having excellent toughness, chipping resistance, strength and workability by subjecting a mixture composed of powders of specific compsns. to pressure sintering under and at a specific pressure and temp.

**SOLUTION:** The compsn. of the mixture is composed, by volumetric %, of 30 to 65% cubic boron nitride powder, 20 to 50% aluminum oxide powder, 0.1 to 10% metallic aluminum powder, 0.1 to 8%  $\geq$  1 kinds of compd. consisting of any of Li, Na and K and oxygen and silicon and 10 to 30% powder of  $\geq$  1 kinds of any of the carbide, nitride and boride of Si and periodic table group 4A, 5A, 6A elements.

The mixture is subjected to pressure sintering under 100MPa pressure and a 1000 to 1500°C. As a result, the need for a coating stage requiring costly devices is eliminated and highly dense sintered compacts are produced relatively easily.

**LEGAL STATUS**

[Date of request for examination]

[Date of sending the examiner's decision of rejection]

[Kind of final disposal of application other than the examiner's decision of rejection or application converted registration]

[Date of final disposal for application]

[Patent number]

[Date of registration]

[Number of appeal against examiner's decision of rejection]

[Date of requesting appeal against examiner's decision of rejection]

[Date of extinction of right]